

TECHNICAL DATE SHEET

BIOFLEX

BASE MATERIAL: Copolyester

PROPERTIES

	PROPERTIES	VALUE	METOD AND CONDICTION
PHYSICAL & MECHANICAL	Density	1,09 g/cm ³	D792
	Hardness/ Flexure Modulus	27 SHORE D	ASTM D2240
	Tensile strength at break	16 Mpa	ISO D638
	Tensile Modulus	35 Mpa	ASTM D790
	Tensile Elongation	800%	ISO D638
THERMAL	Melting point	185°C	ASTM D3417
	Glass transition temperature	-70°C	/
	Viscat Softening Temperature	/	D3418
	Electrical properties:		
	Volume resistivity	> 10 ¹³ Ohm.cm at 23°C	ASTM D 257
	Dielectric strength	16 kV/mm at 23°C	ASTM D 149

SUGGESTED PRINTER SETTING

	VALUE	UNIT
Extruder Temperature	210 – 230	°C
Print Speed	40 – 60	mm/sec
Bed Material	0 – 70	°C

PRODUCT DETAILS & CERTIFICATION

Diameter	1,75 mm 2,85 mm	Tollerance ± 0,05mm Tollerance ± 0,10mm
REACH compliant		ND
FDA compliant		ND
ROHS certified		ND

The information supplied in relation to our products recommendations or otherwise, is collected from source considered to be dependable or internally developed. Ciceri de Mondel Srl assumes no liability and makes no warranties of any kind about the accuracy of this datas. The user assumes all responsibility for the use of all information provided and shall.

Filoalfa by Ciceri de Model Srl
Via Galvani 13, 20080
Ozzero (MI)